

VEROLAC

Gloss Alkyd Enamel

Very durable, gloss enamel based on alkyd resins, suitable for interior and exterior use on metallic surfaces. It forms a hard film that retains its gloss and shade unchanged, even if exposed to adverse weather conditions or washed. Due to its special formulation is an excellent anticorrosion finish for all kinds of metallic surfaces. It is easily applied offering high hiding power, excellent levelling properties and providing protection and decoration.



Advantages:

- Perfect anticorrosive finish for all exterior and interior metal surfaces
- Great hardness and hiding power
- Gloss finish and color shades that remain unchanged over time

PRODUCT FEATURES

TECHNICAL CHARACTERISTICS



Viscosity

70 ± 5 KU (ASTM D 562, 25°C)

Density

1,21 ± 0,02 Kg / L (ISO 2811)
for white

Gloss

> 90 units @ 60° (ISO 2813)

COVERAGE



One coat

14-16 m²/L



Two coats

7-8 m²/L

PACKAGING

White, Black, 42 ready-made shades	180 mL	375 mL	750 mL	2,5 L	5 L
Black mat	180 mL	375 mL	750 mL	2,5 L	



FINISH

Mat	Satin	Gloss
✓		
Gloss Finish		

DILUTION



Up to 5%

- For brushing with Brush Solvent T300
- For spraying with Spray Gun Solvent T350

DRYING TIME



Touch dry

2-3 h

Recoat

20-24 h

COLOURS

White, Black, Black mat and 42 ready-made shades



COLOR CARDS - FANDECKS



METAL SURFACES

APPLICATION

APPLICATION FIELD

For all kinds of metal surfaces.

PREPARATION



Surfaces should be cleaned with Brush Solvent T300, be smooth and dry, free from dust, grease or rust and sanded.



Metal surfaces should be coated with an anticorrosive primer (Anti-Rust Primer, Minio Primer or Metal Primer).



Glossy metal surfaces (aluminum, galvanized steel etc) should be first coated with Primer for Glossy Surfaces or Wash Primer.



STEPS

1

Dilute up to 5% for brushing with brush solvent T300 or for spraying with spray gun solvent T350 and stir well before use.

2

Apply the first coat by brush, roller or spray gun.

3

Recoat after 20-24 hours.

TIPS

- Application at 5-35°C and <80% RH. For exterior use, don't apply if there is a risk of rain/frost in the next 48 hours.
- Clean rollers, brushes with Brush Solvent T300 and then with soapy water or detergent. Use Spray Gun Solvent T350 to clean spray guns.
- Allow at least 30 days before cleaning

- and washing newly painted surfaces with Verolac.
- Minimize paint wastage by estimating how much paint you will need.
- Recover unused paint for re-use. After paint application, seal the container and store it for future use.
- Do not dispose of liquid waste into

ground water table. Unused paint requires special handling for safe disposal.

ADDITIONAL INFORMATION

VOCs (Volatile Organic Compounds)



"One-pack performance coatings". VOC content limit **500 g/L**. Maximum VOC content **495 g/L** VOCs (ready for use product).

PRECAUTIONS



Please read carefully the labelling mentioned on the can before use. For detailed instructions on hazards and safety in use the Safety Data Sheet is available upon request. Poisons Control Centre Tel. : +30 210 7793 777

STORAGE



5°C-38°C

Keep containers closed in a cool and dry area.

The above technical data, information and instructions are based on our long experience and laboratory tests and are intended only to describe the product and determine its application. However, the end user should check the suitability of the product for its intended use. Our company guarantees the quality of the product itself, and in any case bears no responsibility for any damage or damage caused if the product is not used properly and in accordance with its instructions for use. The company has the right to revise this technical data sheet without any prior notice.

+30.210.5589.400
TECHNICAL SUPPORT

ISO 9001
14001
CERTIFIED 45001

