

EUMARIA CLASSIC

Soft antifouling

Soft organotin-free antifouling. Contains copper (I) oxide and specific biocides, protects submerged areas against bacteria, algae, seaweed, shellfish and generally adherent organisms. Suitable for any kind of boats or vessels, cruising at speeds up to 20 knot.



Advantages:

- Contains Copper (I) based biocides and specific biocides
- Ideal for hulls made of polyester, wood, steel, aluminum

PRODUCT FEATURES

PHYSICAL PROPERTIES



Specific gravity:

1,34 – 1,41 Kg/L
(depending on shade)

Volume solids (%):

~50%

FINISH

Mat	Satin	Gloss
✓		
Mat Finish		


DILUTION



Ready to use

If required, thin up to **10%** with solvent T-350.

COVERAGE



Per coat

8-10 m²/L

DRYING TIME



For complete drying require:

- 16 hours at 10°C
- 8 hours at 15°C
- 4 hours at 25°C
- 3 hours at 35°C

Painted surfaces can be safely used by humans and animals after drying time.

COLOURS

Black, Oxide red and Blue



PACKAGING

Shades:	750 mL	2,5 L	20 L
---------	--------	-------	------



APPLICATION

PREPARATION



Surface must be completely clean and dry at the time of application and the temperature must be above the dew point to avoid condensation of moisture.



Make sure there is adequate ventilation during application and drying.



To paint over old antifouling, abrade surface, remove dirt, algae, seaweed shellfish etc. and rinse thoroughly with fresh water at high pressure.

If priming is required (old antifouling unknown or in poor condition) use Eumaria Vinyl Primer one Component.

STEPS

1

Approx. 8-10 m²/L per coat.

2

Apply by roller, brush or airless spray.

3

Cleaning of tools: Tools must be cleaned immediately after use with solvent T-350.

TIPS

• Launching: After the final coat is completely dry. But it can be delayed for a few days at a low temperature - or when it is not exposed to sunlight - up to two weeks without affecting the antifouling properties.

• Recoatability time: 2-3 coats of 100 microns wet film thickness are required. Recoat after the previous layer is completely dried. (Consult the detailed Eumaria Technical Guide).

• NOTE: Stir well before use. Avoid application in direct sunlight and temperatures below 10°C, above 35°C and / or relative humidity above 80%.

ADDITIONAL INFORMATION

VOCs (Volatile Organic Compounds)



<470g/L

PRECAUTIONS



Please read carefully the labelling mentioned on the can before use. For detailed instructions on hazards and safety in use the Safety Data Sheet is available upon request. Poisons Control Centre Tel. : +30 210 7793 777

STORAGE



Maximum storage time 2 years from the production date. Keep containers closed in a cool, dry, well ventilated place, away from solar radiation in temperatures between 5°C and 38°C and/or relative humidity less than 80%.

The above technical data, information and instructions are based on our long experience and laboratory tests and are intended only to describe the product and determine its application. However, the end user should check the suitability of the product for its intended use. Our company guarantees the quality of the product itself, and in any case bears no responsibility for any damage or damage caused if the product is not used properly and in accordance with its instructions for use. The company has the right to revise this technical data sheet without any prior notice.

+30.210.5589.400
TECHNICAL SUPPORT

