EUMARIA VINYL PRIMER



Chlorinated vinyl one component primer with aluminum flakes.
Suitable barrier/sealer coat over incompatible or unknown antifoulings.
As an intermediate/sealer coat between epoxy primer and topcoat or Antifouling.



Packing Size



750mL, 2.5L, 20L

Physical Properties



Specific gravity: ~1,19 - 1,23 Kg/L

Volume solids (%): ~45%

Finish:

Mat

Shades:

Silver

VOC:

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category A/i "One-pack performance coatings", Type SB): 500 g/L. This product contains maximum 499q/L VOCs (ready for use product).

Instructions for use



⊘ Spreading rate:

8-12 m²/L per coat on properly prepared surfaces

Touch dry after 2 h @ 5°C, 1 h @ 15°C 40min @ 25°C, 15min @ 35°C (80-120µm wet film thickness).

⊘ Cleaning of tools:

Tools must be cleaned immediately after use with solvent T-350.

⊘ Application:

Apply by roller, brush or airless spray gun.

⊘ Thinning:

Ready for use. If required, dilute 5% - 10%. Use solvent T-350.

\odot Recoatability time:

2 h @ 5°C, 2 h @ 15°C, 1h @ 25°C, 40min @ 35°C (80-120µm wet film thickness).

*Note: Do not apply in direct sunlight and temperatures below 10°C, higher than 35°C and / or relative humidity above 80%. In confined spaces, make sure there is adequate ventilation during application and drying.

Surface preparation



Surfaces must be clean and dry and the temperature must be above the dew point to avoid condensation of moisture. For use over old antifouling, remove dirt, algae, seaweed shellfish etc. and wash thoroughly with fresh water at high pressure.

Storage



Keep containers closed in a cool, dry, well ventilated place, away from solar radiation in temperatures 5°C and 38°C and/or relative humidity less than 80%.

Health, safety & environmental issues



Consult the Safety Data Sheet.