

# **GRANIKOT FIRE RESISTANT**

# Non-Combustible Plaster

Superior quality fiber reinforced, noncombustible (class A2-s1,d0), acrylic plaster facade, weather- resistant with exceptional UV resistance radiation properties. It has excellent adhesion, firmness and elasticity. It's used to

protect and decorate exterior and interior surfaces (plaster, concrete, facade thermal insulation systems). Certified with the CE marking according to EN 15824.



Fire

Protection

GRANIKOT

FIRE RESISTANT

vitex)



#### **Advantages:**

- Certified class A2-s1, d0 to reaction to fire
- Exceptional resistance properties against weather and UV radiation
- Excellent adhesion, firmness and elasticity

## **PRODUCT FEATURES**

## **TECHNICAL CHARACTERISTICS**



25.000-30.000 cps (BROOKFIELD sp.7/50rpm, 25°C)

**Density** 1,90 ± 0,02 Kg / L (ISO 2811)

## COVERAGE

## Flat render:

- Granulometry 1,0 mm = 1,7-2,2 Kg/m<sup>2</sup>
- Granulometry 1,5 mm = 2,0-2,5 Kg/m<sup>2</sup>
- 3000 + White and unlimited number of shades through Vitex Coloring System

**COLOURS** 

DILUTION

**DRYING TIME** 

Water

**Touch dry** 4-6 h

0-2%






## **COLOR CARDS - FANDECKS**



### PACKAGING






## APPLICATION

## **APPLICATION FIELD**

For the protection and decoration of exterior and interior surfaces (plaster, concrete, facade thermal insulation systems- ETICS)

## PREPARATION





Stir well with a mechanical drill, before application and at regular intervals during application. If required, dilute with maximum 2% of water.

Apply by stainless steel spatula and use a plastic trowel for forming the final texture. Depending on the weather conditions, the structuring of the plaster should be done within 5 -15 minutes after applying the plaster in order to achieve the proper Flat texture.

## TIPS

- Application at 5-35°C and <80% RH. For exterior use, do not apply if there is a risk of rain/frost in the next 48 hours and strong wind conditions.
- Weather conditions are particularly important for the quality and aesthetic effect of plaster. Very high temperatures reduce the open time of the plaster, while rain on a fresh painted surface will cause deterioration of the final result.
- Avoid direct and uneven exposure to sun

irradiation to prevent non-uniform drying.
In case structuring starts after 15 minutes of plaster application and the plaster has already begun drying, then the Flat texture might become defective and uneven during the structuring.

• It is dry to touch in 4-6 hours and in depth in 24 hours at + 20°C and 65% relative humidity. Complete cure is achieved after about 14 days. These times vary depending on weather conditions (relative humidity and temperature).

- Tools must be cleaned immediately after use with water and if needed, with soapy water or detergent.
- Recover unused material for re-use. After plaster application, seal the container and store it for future use.

• Do not dispose of liquid waste into ground water table. Unused material requires special handling for safe disposal.

## **ADDITIONAL INFORMATION**

#### **VOCs** (Volatile Organic Compounds)



"Exterior walls of mineral substrate". VOC content limit **40 g/L**. Maximum VOC content **39 g/L** VOCs (ready for use product).

## STORAGE



#### 5°C-38°C

Containers must be kept closed in a shady place away from direct sunlight, maximum 24 months from date of production.

### PRECAUTIONS



Please read carefully the labelling mentioned on the can before use. For detailed instructions on hazards and safety in use the Safety Data Sheet is available upon request. Poisons Control Centre Tel. : +30 210 7793 777

The above technical data, information and instructions are based on our long experience and laboratory tests and are intended only to describe the product and determine its application. However, the end user should check the suitability of the product for its intended use. Our company guarantees the quality of the product itself, and in any case bears no responsibility for any damage or damage caused if the product is not used properly and in accordance with its instructions for use. The company has the right to revise this technical data sheet without any prior notice.





Version: 06.2023 (This datasheet supersedes all previous versions)